



PLASTIC RECYCLING, INC.

Plastic Waste Specialists

RECYCLED
COMPOUNDS

TECHNICAL DATA SHEET

PP

COPP 30-01 BLACK 000

P/E

Polypropylene copolymer unfilled, high flowability specific for injection moulding, black color.

Description

Injection Molding

USA, Mexico, Europe

Processing Methods

Availability

V2-10-24

Used for rigid packaging applications

ASTM

Typical Applications

Test Methods

TYPICAL PROPERTIES

Physical	Method	Conditions	Value	Unit
Melt mass-flow rate	ASTM D1238 Procedure B	230°C - 2.16 kg	30.0	g/10'
Density	ASTM D792 Method A	-	940	kg/m³
Ash content	Internal Method	475°C - 15 min	4.0	%

Mechanical	Method	Conditions	Value	Unit
Flexural modulus	ASTM D790	73°F - 0.05 in/min	160000	psi
Flexural strength	ASTM D790	73°F - 0.05 in/min	3800	psi
Tensile Modulus	ASTM D638	73°F - 0.05 in/min	180000	psi
Tensile stress at Yield	ASTM D638	73°F - 2 in/min	2800	psi
Tensile stress at Break	ASTM D638	73°F - 2 in/min	2175	psi
Elongation at Yield	ASTM D638	73°F - 2 in/min	6.0	%
Elongation at Break	ASTM D638	73°F - 2 in/min	55.0	%
Izod Pendulum Impact Resistance	ASTM D256	73°F	1.2	ft*lb/in
Izod Pendulum Impact Resistance	ASTM D256	-22°F	0.5	ft*lb/in

Thermal	Method	Conditions	Value	Unit
Deflection Temperature Under Load	ASTM D648	(66 psi, Unanneled)	180	°F
Vicat softening temperature	ASTM D1525	Loading 2 - Rate A (50N-50 C/h)	145	°F
Horizontal Combustibility	FMVSS302	-	OK	-

It is the responsibility of our customers to check if the materials supplied and articles made out of it are suitable for the intended use and comply with all applicable regulations and requirements. All information supplied by or on behalf of PRI in relation to its products in the nature of data, recommendations or otherwise, is supported by research and believed reliable, PRI assumes no liability whatsoever in respect of application, processing or use made of the afore-mentioned information or products, or any consequence thereof. The user undertakes all liability in respect of the application, processing or use of the afore mentioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to PRI for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the afore-mentioned information or products by the user.